

RA330® is the workhorse of the heat resistant alloys. It has good strength, carburization and oxidation resistance to 2100°F. These properties are enhanced by a nominal 1.25% silicon addition. RA330 has been designed to withstand the thermal shock of liquid quenching. RA330 finds wide application in high temperature industrial environments where good resistance to the combined effects of carburization and thermal cycling is a prime requisite. RA330 remains fully austenitic at all temperatures and is not subject to embrittlement from sigma formation.

RA330 is worked by forming and machining procedures similar to those used with the austenitic stainless steels or nickel-chromium alloys. Forming at room temperature is suggested whenever possible. Heat treatment is not necessary after most forming or welding operations. When required, the suggested full anneal is 1900-2050°F, rapid air cool or water quench. RA330 may be readily welded using RA330-04 weld fillers of matching composition. Do not use AWS ER330. Keep interpass temperatures low, do not preheat, do use reinforced stringer beads. Machinability rating 20-25% of B1112.

**Specifications**

UNS: N08330 W. Nr./EN: 1.4886, 10095 ASM: 5592, 5716 ASME: SB-536, SB-511, SB-535, SB-710  
 ASTM: B 536, B 511, B 512, B 535, B 546, B 710, B 739

**Chemical Composition, %**

	Cr	Ni	Mn	Si	Cu	P	S	C	Fe
MIN	18.0	34.0	-	1.0	-	-	-	0.04	-
MAX	20.0	37.0	2.0	1.5	1.0	0.03	0.03	0.08	*bal

**Physical Properties**

Density: 0.287 lb/in<sup>3</sup> Melting Range: 2450 - 2540°F

Temperature, ° F	70	1400	1600	1800
Coefficient* of Thermal Expansion, in/in°F x 10 <sup>-6</sup>	-	9.7	9.8	10.0
Thermal Conductivity Btu • ft/ft <sup>2</sup> • hr • °F	7.2	13.7	14.2	14.7
Electrical Conductivity, 68°F (20°C), %IACS	28.5	21.0	19.5	18.0

\*70°F to indicated temperature.

**Mechanical Properties**

Typical Properties, Mill Annealed

Temperature, ° F	70
Ultimate Tensile Strength, ksi	85.0
0.2% Yield Strength, ksi	39.0
Elongation, %	47
Reduction of Area, %	65
Hardness, Rockwell B	70-85
ASTM Grain Size	4-7
Erichsen Cup Depth, 0.025 in sheet	0.3937 in
Poisson's Ratio	0.297

**Features**

- Oxidation resistant to 2100°F
- High creep-rupture strength
- Resistant to carburization and nitriding
- Resistant to thermal shock
- Good strength at elevated temperatures
- Metallurgical stability
- Chloride ion stress corrosion cracking resistance

**Applications**

- Furnace containers - carburizing, carbonitriding, annealing malleablizing
- Muffles, retorts
- Bar frame heat treating baskets
- Quenching fixtures
- Radiant tubes
- Salt pots, both neutral and cyanide
- Furnace fans and shafts
- Conveyors
- Hot pressing platens
- Tube hangers for crude oil heaters and steam boilers

**Mechanical Properties Cont.**
**Short Time Elevated Temperature Tensile Properties**

Temperature, ° F	Ultimate Tensile Strength, ksi	0.2% Yield Strength, ks	Elongation, %
1000	71	25	46
1100	66.4	24.2	46
1200	56.7	22	43
1300	44.3	21	69
1400	35.9	20.7	78
1500	26.8	17.3	56
1600	21.1	15.4	79
1800	10.4	8.5	79
2000	3.2	2.0	28

**Typical Creep-Rupture Properties**

Temperature, ° F	1400	1600	1800	2000
Minimum Creep 0.0001%/Hour, ksi	3.6	2.1	0.5	-
10,000 Hour Rupture Strength, ksi	4.3	1.7	0.63	0.28

**TECHNICAL QUESTIONS?**
**OUR TEAM OF METALLURGISTS ARE HERE TO HELP.**
**PHONE:** 1.800.521.0332 (Ask for a Metallurgist)

**EMAIL:** metallurgical-help@rolledalloys.com

*Additional resources available at [rolledalloys.com/technicalresources/](http://rolledalloys.com/technicalresources/)*


*Rolled Alloys and RA are registered trademarks of Rolled Alloys. The data and information in this printed matter are believed to be reliable. However, this material is not intended as a substitute for competent professional engineering assistance which is a requisite to any specific application. Rolled Alloys makes no warranty and assumes no legal liability or responsibility for results to be obtained in any particular situation, and shall not be liable for any direct, indirect, special, or consequential damage therefrom. This material is subject to revision without prior notice.*