

Alloy	Total Life, days
RA333	197 (end of test—no failure)
600	112
Nickel 200	51
C-276	40
601	14